



The Alsa Corporation

The Worlds Most Exotic Finishes

Base PEARLS

Base Pearl
Urethane Midcoat

Product Number

ABP

Description

Urethane Midcoat

Reducer

AMR-2712

Description

Medium Urethane
Reducer

Description

Base Pearl is a medium solids color shifting Midcoat designed to shift between colors..

Surface Preparation

1. Wash area thoroughly with soap and water to remove contaminants that solvent based cleaners cannot remove effectively.
2. Clean repair area with Wax and Grease Remover For maximum adhesion, treat bare metal with a quality metal conditioning system or prime with AEP-3027 Epoxy Primer, ASEP-332 Self Etching Wash Primer.
3. Fill imperfections with APS -2712 primer surfacer. Final sand surface wet or dry with 600 grit paper or finer before applying basecoat.

Mixing Ratio (1:1)

Mix 1 part ABP to 1 part AMR-2712.

Application

1. Apply ABP-14 White or color of your choice.
Apply 2-3 medium-wet coats at 25 psi allowing 10-15 minute flash between coats.

Dry times at 77° F

Dust Free in 5 minutes

Tack Free in 10 minutes

Force Drying

Flash time @ 77° F 5 Minutes

Bake Time @140°F 10 Minutes

Allow 15-30 minutes before applying any Alsa Clear of your choice