



# The Alsa Corporation

The Worlds Most Exotic Finishes

## Product Number

CB-3012

## Reducer

AMR-2712

CB-3012

Color Blender

## Description

Color Blender

## Description

Medium Reducer

## **Description**

CB-3012 Color Blender is intended for use as a tool to blend with Pearls, Candy Concentrates, and Flakes.

## **Surface Preparation**

Old cured finishes must be thoroughly cleaned and sanded in areas where CB-3012 will be applied

## **Mixing Ratio (1:1)**

Mix 1 part CB-3012 to 1 part AMR-2712.

## **Application**

Adjust air pressure at the gun to 35-45 psi for gravity or siphon feed application or 5-7 psi at the cap for HVLP.

Apply 1-2 light to medium coats of the color blender onto the blend area, extending each coat a little further each time. Allow 5-10 minutes between coats.

## **Dry times at 70° F**

Dust Free in Time 10 minutes

Tack Free Time in 15 minutes

Tape Free Time in 45 minutes

## **Equipment Clean-up**

Clean equipment immediately after use with AMR-2712

## **Technical Data**

Viscosity #2 Zahn (RTS)	18-20 sec.
Volume Solids(RTS)	12%
Film Build Per coat	0.5 Mil
Disposal/Safety	See MSDS
Humidity Resistance	Excellent