



The Alsa Corporation

MYC-100,200,300,400
Urethane Midcoat

Product Number
MYC-100,200,300,400

Description
Urethane Midcoat

Reducer
AMR-2712

Description
Medium Urethane
Reducer

Description

Mystic is a medium solids color shifting Midcoat designed to shift between colors..

SURFACE PREPERATION

1. Wash area thoroughly with soap and water to remove contaminates that solvent based cleaners cannot remove effectively.
2. Clean repair area with Wax and Grease Remover For maximum adhesion, treat bare metal with a quality metal conditioning system or prime with AEP-3027 Epoxy Primer, ASEP-332 Self Etching Wash Primer.
3. Fill imperfections with APS -2712 primer surfacer. Final sand surface wet or dry with 600 grit paper or finer before applying basecoat.

Mixing Ratio (4:1)

Mix 1 part MYC100, 200, 300, or 400 to 1 part AMR-2712.

Application

1. Apply Alsa Jet Black Stylin Basecoat ASB-13.
Apply 2-3 medium-wet coats at 25 psi allowing 10-15 minute flash between coats.

Dry times at 77° F

Dust Free in 5 minutes

Tack Free in 10 minutes

Force Drying

Flash time @ 77° F 5 Minutes

Bake Time @140°F 10 Minutes

Allow 15-30 minutes before applying any Alsa Clear of your choice